

HIGH MOLECULAR WEIGHT PVC

VICIR S1500

Description

VICIR S1500 is a very high molecular weight polyvinyl chloride grade, manufactured by a suspension polymerisation process. It is a highly porous polymer with a very good plasticizer absorption, easy processing characteristics, high thermal stability, good electrical properties and low fish-eyes level.

Property	Value*	Unit	Test Method
K-value	74	-	ISO 1628-2
Bulk density	0.470	g/cm ³	ISO 60
Size Analysis			ISO 13320-1
> 250µm	≤ 2.5	%	
< 63µm	≤ 4	%	
Volatile content	≤ 0.3	%	ISO 1269
Plasticizer absorption	37	%	ISO 4608
Residual Vinyl Chloride	< 1	ppm	ISO 24538

Typical values

* Data obtained on representative samples of this grade. These values are typical, for guidance only and must not be used as a basis for specifications.

Applications

VICIR S1500 is recommended for a range of clear and opaque flexible products, such as calendered films and sheets, flexible extruded pipes and profiles and injection moulded goods. Due to its dielectrical properties, it is especially suitable for insulating and sheating wires and cables. Also suitable for products where excellent initial colour or transparency or physical-mechanical properties are required such as footwear.

Storage

The resin must be stored in a dry area under moderate temperature conditions (maximum 30 °C) and avoid direct UV light exposure.

Shipping

In general, shipping of the resin is done in bulk. Most common bulk transport modes are silotrucks and pressurized containers for rail and sea transport. VICIR S1500 is available in 25 kg multi-ply paper bags as well as in flexible containers (FIBC's) of ca. 750 or 1000 kg

Safety

For information on the safety precautions please refer to our safety data sheet (SDS) of VICIR S-PVC. The SDS can be sent on request.

Companhia Industrial de Resinas Sintéticas, CIRES, Lda Rua da CIRES, nº 8 3860-160 Avanca, ESTARREJA PORTUGAL Tel: +351 234 811 200 Fax: +351 234 811 204 E-mail: cires@cires.pt Home: www.cires.pt

Technical Datasheet S1500 - English Revision date - December 2019

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents. We reserve the right to information at any time without prior notification. The version available in CIRES website www.cires.pt should be considered as the valid document.